



POLYASPARTIC 92 LOW ODOR | FC

Hit Tight Deadlines

POLYASPARTIC 92 LOW ODOR | FC is a UV-resistant, 2-component, 100%-solids system. It is best applied in low temperatures with low relative humidity. At full cure, this system withstands extreme temperatures from (-)20 to 200°F.

ADVANTAGES

- Meets USDA, FDA, EPA, and SCAQMD Standards
- Eligible for LEED Points: Made in California from Partially Recycled Materials
- Adhesion to Concrete, Wood, Metal, Non-glazed Tiles
- Antibacterial
- Extreme Temperature Resistance, (-)20–200°F
- Fast Cure
- Low Maintenance
- Low Odor Polyaspartic
- Scratch Resistance
- UV Resistance
- Waterproofing

SUGGESTED USES AND APPLICATION AREAS

- Primer
- High UV-Resistant Top Coat
- Decorative Systems
- Industrial, Healthcare, Commercial, Government, Institutional, and Residential

KRETUS® SYSTEMS

- Color Chip
- Color Quartz
- Color Splash
- ESD (Static Control)
- Industrial Sand
- Top Shelf® Metallic
- UPC 1-Coat
- Waterproof Decking

For all KRETUS® systems, see kretus.com/systems.

FINISH AND COLOR

- High Gloss, Clear
- Opaque when Pigmented (see Color Charts at kretus.com/color-charts)

PRECAUTIONS AND LIMITATIONS

- **Prime Coat:** A prime coat may be required if stem walls are highly absorbent, if outgassing is suspected or prevalent, or if concrete is very porous or in poor condition. All concrete repairs must be completed before installing any system.
- DO NOT apply single coat greater than 14 mils thick (114 square feet per gallon).
- DO NOT let material puddle on floor. This may cause white spots to appear when coating cures.
- **Application temperatures:** For best results, apply when application temperatures and relative humidity are low. Material cures faster as temperature and humidity increase and cures slower as they decrease. If application temperatures exceed those recommended, contact your KRETUS® Technical Representative.

- Apply material when temperature is decreasing—adhere to the KRETUS® Dew Point Calculation Chart available at kretus.com/project-planning. DO NOT apply under direct sunlight. DO NOT install under inclement weather conditions.
- Complete samples and onsite mockups to ensure desired results are achieved.
- Coverage rates are for estimating purposes only. Factors such as waste, unusual/abnormal substrate conditions, and other unforeseen jobsite conditions may affect actual product yields and are the responsibility of the installer.

COMPONENTS

Standard Kit

- Part A: Polyaspartic 92 Low Odor FC, 1 gal
- Part B: Polyaspartic 92 Low Odor B, 1 gal

Bulk Kit

- Part A: Polyaspartic 92 Low Odor FC, 5 gal
- Part B: Polyaspartic 92 Low Odor B, 5 gal

Larger kits may be available through KRETUS® distributor.

SAFETY, TESTING, AND WARRANTY

- **Safety:** Personal protective equipment and safety conditions must be considered before using any product. Review all relevant and current documentation including Safety Data Sheets (kretus.com/safety-data-sheets).
- **Testing:** Before installation: Test and look for any unknown site conditions and/or defects. To ensure desired results are achieved, the system should be tested in a small area on site before full installation begins.
- **Warranty:** For warranty to be upheld, Pre- and Post-Job Checklists (kretus.com/project-planning) must be completed.

STORAGE AND APPLICATION TEMPERATURES

Ideal Storage Environment	Dry, Out of Direct Sunlight, 60-80°F
Material Temperature During Application	50-70°F and 5°F Above Dew Point
Minimum Substrate Temperature During Application	5°F Above Dew Point
Recommended Application Temperature	<80°F, <35% RH (Relative Humidity)

Average Application Time

Ambient Temperature	<80°F, 35% RH	50°F, 30% RH	50°F, 75% RH	70°F, 50% RH	90°F, 20% RH	90°F, 80% RH
Working Time	15-20 min	20-25 min	15-20 min	15-20 min	10-15 min	5-10 min
Recoat Window	3-24 hrs.	6-24 hrs.	3-24 hrs.	3-24 hrs.	3-24 hrs.	1-6 hrs.
Return to Service (Foot Traffic)	24 hrs.	24 hrs.	24 hrs.	24 hrs.	24 hrs.	6 hrs.
Full Cure (Vehicle Traffic)	3 days	7 days	7 days	3 days	3 days	3 days

SURFACE PREPARATION

Before installing any coating, the substrate must be sound, meaning all necessary concrete repairs have been completed. It must be clean, dry, and free of any contaminants, moisture, materials, or particles that may hinder material's adhesion to the substrate. If applying directly over concrete, the substrate must be mechanically profiled to ICRI CSP 3. Different projects may require a different concrete surface profile. Adhere to International Concrete Repair Institute current standards.

MIXING AND APPLICATION

Standard Kit Mix Ratio	A:B = 1 gal:1 gal
Poly Colorant	16 oz per standard kit
Viscosity Reducer	1-2 qts. per standard kit

Mixing Drill	low-RPM, low-torque drill with Jiffy double-bladed mixer
Mixing Drill When Combining With Large Aggregates	high-RPM, high-torque drill with Jiffy double-bladed mixer
Mixing Directions	Mix Part A until color and consistency are uniform. Add Part B and mix for 2 minutes or until color and consistency are uniform.
Mixing Directions With Colorant, Pigment, or Matting Additive	Mix Part A with additive until color and consistency are uniform. Add Part B and mix for 2 minutes or until color and consistency are uniform.
Mixing Directions With Viscosity Reducer, Aggregate, or Anti-Slip	Mix Part A and Part B for 1 minute or until color and consistency are uniform. Add additive and mix for 1 minute or until color and consistency are uniform.

Coverage Rates

Application	Coverage Rate
Base Coat, 8-12 mils	135–200 SF/gal
Broadcast System Cap Coat Over 1/4" Color Chip	125–200 SF/gal
Broadcast System Cap Coat Over 30-Mesh Industrial Sand	90–100 SF/gal
Broadcast System Cap Coat Over F-grade or 40-S Color Quartz	90–100 SF/gal
Prime Coat	300–400 SF/gal
Top Coat, 4-5 mils	300–400 SF/gal
Top Coat, 8-12 mils	135–200 SF/gal

Premeasure components to make sure you are using the correct mix ratio. Combine components according to mix instructions. Continue mixing until the coating's consistency is uniform. The coating must remain thoroughly mixed during the application.

Keep a wet edge while applying product. Wear spiked shoes when walking on material. For more applications and coverage rates, see KRETUS® General Overview (kretus.com/product-general-overviews).

PROPERTIES WHEN FULLY CURED

PROPERTIES	TEST METHOD	TYPICAL VALUES
Abrasion Resistance	ASTM D4060	15 mg loss
Adhesion Strength	ASTM D4541	400 psi, 100% Concrete failure
Adhesion Strength	ASTM D4541	n/a, vinyl failure
Adhesion Strength	ASTM D4541	n/a, natural quartz failure
Adhesion Strength	ASTM D4541	n/a, color quartz failure
Coefficient of Friction - Dry	ASTM D2047	0.7
Coefficient of Friction - Wet	ASTM D2047	0.6
Flame Spread/ Critical Flux	ASTM E648	Class 1
Flame Spread/ Rate of Burning	ASTM D635	Self-extinguishing
Flexibility/ Mandrel Bend	ASTM D522	Passes 1/8-in.
Gloss, 60°	ASTM D523	90
Hardness (König Hardness)	ASTM D4366	150
Impact Resistance	ASTM D2794	120 in-lbs
Indoor Air Quality	CA 01350	Compliant
Microbial Resistance	ASTM G21	Passes, 0 growth
Tensile Elongation at Break	ASTM D2370	5%
Tensile Strength	ASTM D2370	6,000 psi

UV Resistance	ASTM D4587	High (Level 3)
Water Absorption	ASTM D570	<0.05
Yellowing Resistance	ASTM G154	< 3.0 ΔE, gray (color tested for visible changes)

CHEMICAL AND STAIN RESISTANCE

1 = Best for chemical resistance: Chemical has no adverse effects on fully cured coating; remove within 24 hours.

2 = Low potential for stain: Chemical has no adverse effects on fully cured coating if removed within 24 hours.

3 = High potential for stain or degradation: Chemical must be removed within 24 hours of exposure.

NR = Not recommended

Acetic Acid (Component of Vinegar), 10%	1	Methanol	1
Acetic Acid, 30%.....	2	Methylene Chloride	NR
Acetone.....	1	MIBK (Methyl Isobutyl Ketone).....	1
Ammonia, 30%.....	1	Mineral Oil	1
Ammonium Hydroxide, 30%	1	Motor Oil, SAE 30	1
Antifreeze (Coolant).....	1	Mineral Spirits.....	1
Benzene (Component of Crude Oil)	1	Mustard, Yellow	1
Benzyl Alcohol	1	Nitric Acid, 30%	NR
Betadine, 11%	1	Oleic Acid	1
Boric Acid, 4%	1	Oxalic Acid, 10%.....	1
Brake Fluid, DOT 3	1	Phosphoric Acid, 20%	2
Chromic Acid, 10%.....	1	Potassium Hydroxide, 30%	
Chromic Acid, 30%.....	1	(Alkaline Batteries, Soap Manufacturing)	1
Citric Acid, 30%	1	Propylene Glycol	1
Ethanol, 95%.....	1	Silver Nitrate, 20% (Photo Labs)	3
Ethyl Acetate, 99% (Food/Beverage Facility)	1	Hydraulic Fluid (Aviation), Skydrol LD-4	2
Formaldehyde, 37%	3	Sodium Chloride, 20%.....	1
Premium Gasoline.....	1	Sodium Hydroxide (Caustic Soda), 50%	1
Hydraulic Fluids		Sodium Hypochlorite (Bleach), 10%	1
(Machinery, Automobile, Aviation).....	2	Sodium Hypochlorite (Bleach), 30%.....	2
Hydrochloric Acid, 10%.....	1	Sodium Persulfate	
Hydrochloric Acid, 30%.....	3	(Bleaching and Oxidizing Agent)	3
Hydrofluoric Acid, 10%	1	Sulfuric Acid, 37% (Battery Acid)	2
Hydrofluoric Acid, 30%	3	Tannic Acid, 20%.....	3
Hydrogen Peroxide, 10%	1	Tartaric Acid, 10%	1
Hydrogen Peroxide, 50%	1	Transmission Fluid	1
Iodine, 2%	3	Urine, Dog or Cat	1
Isopropyl Alcohol	2	Urea (Nitrogen-Rich Fertilizer).....	1
Jet Fuel.....	1	Vinegar, Distilled	1
Lactic Acid, 30% (Dairy Facility).....	3	Water (Hard Water from Well)	1
Lime Juice	1	Whisky	1
Magnesium Hydroxide.....	1	Wine, Cabernet Sauvignon	1
MEK (Methyl Ethyl Ketone)	1	Xylene	1

Pigments or colorants may affect working times, reduce chemical resistance, or increase potential for stain. Coatings tested at ambient temperature over 1-3 days' exposure to chemical. To ensure desired results are achieved, products should be tested on site before installation.

DISCLAIMER: The information contained in this document is intended for use by KRETUS®-qualified and -trained professionals. This is not a legally binding document and does not release the specifier from their responsibility to apply materials correctly under the specific conditions of the construction site and the intended results of the construction process. The most current valid standards for testing and installation, acknowledged rules of technology, as well as KRETUS® technical guidelines must always be adhered to. The steps given in this document and other mentioned documents are critical to the success of your project.