



POLYURETHANE HS | EZ

Meet Installation Demands at Any Skill Level

POLYURETHANE HS | EZ is a 2-component system that's perfect for high-traffic areas such as forklift loading zones, drive aprons, and commercial walkways. This UV-resistant polyurethane is designed for high-build applications (up to 20 mils) and can be used as a prime, body, and top coat. Bonus: its EZ hardener has a long working time, which decreases the risk of roller and brush marks and makes it easy to install.

ADVANTAGES

- Meets USDA, FDA, EPA, and SCAQMD Standards
- Adhesion to Concrete, Wood, Metal, Non-glazed Tiles
- Antibacterial
- Easy Installation
- Eligible for LEED Points: Made in California from Partially Recycled Materials
- High Impact Resistance
- High Traffic and Hot Tire Resistance
- Low Maintenance
- Low Odor
- Scratch Resistance
- UV Resistance
- Waterproofing

SUGGESTED USES AND APPLICATION AREAS

- Prime, Base, and Top Coats
- Vertical Surfaces
- Industrial, Healthcare, Commercial, Government, Institutional, and Residential

KRETUS® SYSTEMS

- Color Chip
- Color Quartz
- Color Splash
- Epoxy MVR
- ESD (Static Control)
- Industrial Sand
- Top Shelf® Metallic
- Waterproof Decking

For all KRETUS® systems, see kretus.com/systems.

FINISH AND COLOR

- High Shine/Gloss, Clear
- Opaque when Pigmented (see Color Charts at kretus.com/color-charts)

PRECAUTIONS AND LIMITATIONS

- **Prime Coat:** A prime coat may be required if stem walls are highly absorbent, if outgassing is suspected or prevalent, or if concrete is very porous or in poor condition. All concrete repairs must be completed before installing any system.
- DO NOT apply single coat greater than 20 mils thick (80 square feet per gallon).
- DO NOT let material puddle on floor. This may cause white spots to appear when coating cures.
- Complete samples and onsite mockups to ensure desired results are achieved.

- **Application temperatures:** Material cures faster as temperature and humidity increase. Material cures slower as they decrease.
- Application times are based on test results compiled by lab technicians in a controlled setting. All times recorded using 1-quart samples.
- If application temperatures are outside of those recommended, contact your KRETUS® Technical Representative.
- Coverage rates are for estimating purposes only. Factors such as waste, unusual/abnormal substrate conditions, and other unforeseen jobsite conditions may affect actual product yields and are the responsibility of the installer.
- Apply material when temperature is decreasing—adhere to the KRETUS® Dew Point Calculation Chart available at kretus.com/project-planning. DO NOT apply under direct sunlight. DO NOT install under inclement weather conditions.
- For best results, apply when application temperatures and relative humidity are high.
- Recommended for Applicators level 3 and up. (See kretus.com/applicator-skill-level.)

COMPONENTS

Standard Kit

- Part A: Polyurethane HS EZ, 1 gallon
- Part B: Polyurethane HS, 1/2 gallon

Double Kit

- Part A: Polyurethane HS EZ, 2 gallons
- Part B: Polyurethane HS, 1 gallon

Larger kits may be available through KRETUS® distributor.

SAFETY, TESTING, AND WARRANTY

- **Safety:** Personal protective equipment and safety conditions must be considered before using any product. Review all relevant and current documentation including Safety Data Sheets (kretus.com/safety-data-sheets).
- **Testing:** Before installation: Test and look for any unknown site conditions and/or defects. To ensure desired results are achieved, the system should be tested in a small area on site before full installation begins.
- **Warranty:** For warranty to be upheld, Pre- and Post-Job Checklists (kretus.com/project-planning) must be completed.

STORAGE AND APPLICATION TEMPERATURES

| | |
|--|---------------------------------------|
| Ideal Storage Environment | Dry, Out of Direct Sunlight, 60-80°F |
| Material Temperature During Application | 50-70°F and 5°F Above Dew Point |
| Minimum Substrate Temperature During Application | 5°F Above Dew Point |
| Recommended Application Temperature | 60-110°F, <90% RH (Relative Humidity) |

Average Application Time

| Ambient Temperature | 60-110°F, <90% RH | 50°F, 30% RH | 50°F, 75% RH | 70°F, 50% RH | 90°F, 20% RH | 90°F, 80% RH |
|----------------------------------|-------------------|--------------|--------------|--------------|--------------|--------------|
| Working Time | 30-45 min | NR | NR | 30-45 min | NR | 30 min |
| Recoat Window | 6-8 hrs. | NR | NR | 8-36 hrs. | NR | 6-24 hrs. |
| Return to Service (Foot Traffic) | 48 hrs. | NR | NR | 36 hrs. | NR | 24 hrs. |
| Full Cure (Vehicle Traffic) | 7 days | NR | NR | 7 days | NR | 5 days |

*NR=Not Recommended

SURFACE PREPARATION

Before installing any coating, the substrate must be sound, meaning all necessary concrete repairs have been completed. It must be clean, dry, and free of any contaminants, moisture, materials, or particles that may hinder material's adhesion to the substrate. If applying directly over concrete, the substrate must be mechanically profiled to ICRI CSP 3. Different projects may require a different concrete surface profile. Adhere to International Concrete Repair Institute current standards

MIXING AND APPLICATION

| | |
|--|--|
| Standard Kit Mix Ratio | A:B = 1 gal:1/2 gal |
| Poly Colorant | 16 oz per standard kit |
| Viscosity Reducer | 1-2 qts per standard kit |
| Fumed Silica | 1 qt per standard kit |
| Mixing Drill | low-RPM, low-torque drill with Jiffy double-bladed mixer |
| Mixing Directions | Mix A until color and consistency are uniform. Add B and continue to mix for 2 min. |
| Mixing Directions With Colorant | Mix A with colorant until color and consistency are uniform. Add B and continue to mix for 2 min. |
| Mixing Directions With Viscosity Reducer | Mix A with colorant until color and consistency are uniform. Add B and continue to mix for 2 min. |
| Mixing Directions With Anti-Slip or Fumed Silica | Mix A alone or with or without colorant until color and consistency is uniform. Add additive and continue to mix for 1 min. Add B and continue to mix for 1 min. |

Coverage Rates

| Application | Coverage Rate |
|---|----------------|
| Prime Coat | 300 SF/gal |
| Base Coat, 8-12 mils | 100-150 SF/gal |
| Metallic Base Coat, 15-20 mils | 80-105 SF/gal |
| Broadcast System Cap Coat Over 1/4" Color Chip | 125-200 SF/gal |
| Broadcast System Cap Coat Over F-Grade, 40-S, or 30-Mesh Quartz or Sand | 90-100 SF/gal |
| Vertical Coat, 12 mils | 400 SF/gal |

Premeasure components to make sure you are using the correct mix ratio. Combine components according to mix instructions. Continue mixing until the coating's consistency is uniform. The coating must remain thoroughly mixed during the application.

Keep a wet edge while applying product. Wear spiked shoes when walking on material. For more applications and coverage rates, see KRETUS® General Overview (kretus.com/product-general-overviews).

PROPERTIES WHEN FULLY CURED

| PROPERTIES | TEST METHOD | TYPICAL VALUES |
|-------------------------------|-------------|--------------------------------|
| Abrasion Resistance | ASTM D4060 | 15 mg loss |
| Adhesion Strength | ASTM D4541 | 400 psi, 100% Concrete failure |
| Coefficient of Friction - Dry | ASTM D2047 | 0.7 |
| Coefficient of Friction - Wet | ASTM D2047 | 0.6 |
| Flame Spread/ Critical Flux | ASTM E648 | Class 1 |
| Flame Spread/ Rate of Burning | ASTM D635 | Self-extinguishing |
| Flexibility/ Mandrel Bend | ASTM D522 | Passes 1/8-in. |
| Gloss, 60° | ASTM D523 | 90 |
| Hardness (König Hardness) | ASTM D4366 | 150 |
| Impact Resistance | ASTM D2794 | 120 in-lbs |
| Indoor Air Quality | CA 01350 | Compliant |
| Microbial Resistance | ASTM G21 | Passes, 0 growth |

| | | |
|-----------------------------|------------|---|
| Tensile Elongation at Break | ASTM D2370 | 5% |
| Tensile Strength | ASTM D2370 | 6,000 psi |
| UV Resistance | ASTM D4587 | High (Level 3) |
| Water Absorption | ASTM D570 | <0.05 |
| Yellowing Resistance | ASTM G154 | < 3.0 ΔE, gray (color tested for visible changes) |

CHEMICAL AND STAIN RESISTANCE

1 = Best for chemical resistance: Chemical has no adverse effects on fully cured coating; remove within 24 hours.

2 = Low potential for stain: Chemical has no adverse effects on fully cured coating if removed within 24 hours.

3 = High potential for stain or degradation: Chemical must be removed within 24 hours of exposure.

NR = Not recommended

| | | | |
|---|---|--|----|
| Acetic Acid (Component of Vinegar), 10% | 1 | Methanol | 1 |
| Acetic Acid, 30%..... | 2 | Methylene Chloride | NR |
| Acetone..... | 1 | MIBK (Methyl Isobutyl Ketone)..... | 1 |
| Ammonia, 30%..... | 1 | Mineral Oil | 1 |
| Ammonium Hydroxide, 30% | 1 | Motor Oil, SAE 30 | 1 |
| Antifreeze (Coolant)..... | 1 | Mineral Spirits..... | 1 |
| Benzene (Component of Crude Oil) | 1 | Mustard, Yellow | 1 |
| Benzyl Alcohol | 1 | Nitric Acid, 30% | NR |
| Betadine, 11% | 1 | Oleic Acid | 1 |
| Boric Acid, 4% | 1 | Oxalic Acid, 10%..... | 1 |
| Brake Fluid, DOT 3 | 1 | Phosphoric Acid, 20% | 2 |
| Chromic Acid, 10%..... | 1 | Potassium Hydroxide, 30% | |
| Chromic Acid, 30%..... | 1 | (Alkaline Batteries, Soap Manufacturing)..... | 1 |
| Citric Acid, 30% | 1 | Propylene Glycol..... | 1 |
| Ethanol, 95%..... | 1 | Silver Nitrate, 20% (Photo Labs) | 3 |
| Ethyl Acetate, 99% (Food/Beverage Facility) | 1 | Hydraulic Fluid (Aviation), Skydrol LD-4 | 2 |
| Formaldehyde, 37% | 3 | Sodium Chloride, 20%..... | 1 |
| Premium Gasoline..... | 1 | Sodium Hydroxide (Caustic Soda), 50% | 1 |
| Hydraulic Fluids | | Sodium Hypochlorite (Bleach), 10% | 1 |
| (Machinery, Automobile, Aviation) | 2 | Sodium Hypochlorite (Bleach), 30%..... | 2 |
| Hydrochloric Acid, 10%..... | 1 | Sodium Persulfate | |
| Hydrochloric Acid, 30%..... | 3 | (Bleaching and Oxidizing Agent)..... | 3 |
| Hydrofluoric Acid, 10% | 1 | Sulfuric Acid, 37% (Battery Acid) | 2 |
| Hydrofluoric Acid, 30% | 3 | Tannic Acid, 20%..... | 3 |
| Hydrogen Peroxide, 10% | 1 | Tartaric Acid, 10% | 1 |
| Hydrogen Peroxide, 50% | 1 | Transmission Fluid | 1 |
| Iodine, 2% | 3 | Urine, Dog or Cat | 1 |
| Isopropyl Alcohol | 2 | Urea (Nitrogen-Rich Fertilizer)..... | 1 |
| Jet Fuel..... | 1 | Vinegar, Distilled | 1 |
| Lactic Acid, 30% (Dairy Facility)..... | 3 | Water (Hard Water from Well) | 1 |
| Lime Juice | 1 | Whisky | 1 |
| Magnesium Hydroxide..... | 1 | Wine, Cabernet Sauvignon | 1 |
| MEK (Methyl Ethyl Ketone) | 1 | Xylene | 1 |

Pigments or colorants may affect working times, reduce chemical resistance, or increase potential for stain. Coatings tested at ambient temperature over 1-3 days' exposure to chemical. To ensure desired results are achieved, products should be tested on site before installation.

DISCLAIMER: The information contained in this document is intended for use by KRETUS®-qualified and -trained professionals. This is not a legally binding document and does not release the specifier from their responsibility to apply materials correctly under the specific conditions of the construction site and the intended results of the construction process. The most current valid standards for testing and installation, acknowledged rules of technology, as well as KRETUS® technical guidelines must always be adhered to. The steps given in this document and other mentioned documents are critical to the success of your project.