

DIVISION 9: FINISHES

SECTION 09 67 23.13

RESINOUS FLOORING AND COATINGS

10 mils (nominal) Color Splash SBC with SBC Top Coat

PART 1 GENERAL

1.1 SUMMARY

- A. Description: 10 mils (nominal) Solid Color System with Fast Drying and UV Resistant Solvent-Borne Acrylic Base and Top Coat.

1.2 RELATED SECTIONS INCLUDE

- A. Drawings and general provisions of the Contract including General and Supplementary Conditions and Division 1 Specification Sections apply to this Section.
- B. Other Related Sections
 - 1. Section 03 30 00: Cast-in-Place Concrete.
 - 2. Section 03 39 00: Concrete Curing.
 - 3. Section 07 95 00: Expansion Control.

1.3 REFERENCE STANDARDS (MUST USE CURRENT VERSIONS ONLY)

- A. ASTM D7234: Standard Test Method for Pull-Off Adhesion Strength of Coatings on Concrete Using Portable Pull-Off Adhesion Testers
- B. ASTM F710: Standard Practice for Preparing Concrete Floors to Receive Resilient Flooring
- C. ICRI Guide 310.2R Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, Polymer Overlays, and Concrete Repair
- D. RFCI Recommended Work Practices for the Removal of Resilient Floor Coverings

1.4 SUBMITTALS

- A. Product Data: Submit Manufacturer's data sheets and supporting information for each product and process specified including:
 - 1. Approved Applicator
 - 2. Completed Jobsite Checklists and Reports (kretus.com/pre-and-post-job-checklists)
 - 3. Certificate of compliance (quality control document for the goods specified herein)
 - 4. Technical Data Sheets (kretus.com/technical-data-sheets)
 - 5. Safety Data Sheets (kretus.com/safety-data-sheets)
 - 6. Installation Guides (kretus.com/installation-guides)
 - 7. Maintenance and Cleaning Guide (kretus.com/project-planning)
 - 8. Warranty Information
- B. Samples: A 12-inch square sample of the proposed system. Color, texture, and thickness shall be representative of overall appearance of finished system as described in section 1.1A.
- C. Test reports of cured products showing VOC Emission compliance with USGBC LEED Version 4, performed according to California Dept. of Public Health CDPH/EHLB/Standard Method V1.2.

1.5 VERIFIED SAMPLES WITH MOCKUPS

- A. Must be minimum of 50 SF unless otherwise specified by Manufacturer or Architect.
- B. Must employ same materials, tools, and prep methods to be used in project installation.
- C. Product direct to concrete adhesion needs to be verified per ASTM D7234. The results must be greater than 200 psi with concrete failure before proceeding with the installation. Manufacturer reserves the right to request additional mockup and adhesion pull test.

1.6 QUALITY ASSURANCE

- A. Materials used must be manufactured, approved, and distributed by KRETUS® (info@kretus.com, 714-694-2061, kretus.com). No other parties shall be allowed without written approval.
- B. Manufacturer shall have a minimum of 15 years' experience in the production, sales, technical, and installation of material submitted as part of this specification.
- C. Manufacturer shall provide a trained installation professional with knowledge of each product listed herein or any material that has been specified or provided.
- D. Manufacturer-trained professional Applicator. Approved Applicator named must be capable of handling application of similar nature in all phases: surface preparation, application of the product, finishing procedure, safety, and work ethic, and no less than five years' experience with similar projects and complexity.
- E. A recorded (meeting minute submitted) pre-installation conference held between Applicator, General Contractor, Facility Owner, Manufacturer or Manufacturer Representatives, Designer, Architect, and any responsible parties discussed and reviewed for clarification of this specification and any supporting documents relating to this specification or the project itself.
- F. If concrete slabs have history of existing floor failures, identify cause of failure. Identifying the cause(s) may require core samples be taken to and analyzed by a qualified laboratory. Manufacturer must be consulted for core extraction procedures and results.

1.7 WARRANTY

- A. Manufacturer shall provide its standard materials warranty.
- B. Approved Applicator shall furnish warranty for workmanship.

1.8 DELIVERY, STORAGE, AND HANDLING

- A. Packing and Shipping
 - 1. All components of the system shall be delivered to the site free of damage and in the original Manufacturer's packaging, not tampered with, and clearly marked with product type and batch number.
 - 2. All product safety data sheets, bill of lading, and any dangerous goods declaration documents must be included with product and project documents.
- B. Storage and Protection
 - 1. The jobsite shall provide a storage location of all components. The area shall be between 60°F and 80°F, dry, out of direct sunlight and inclement weather, free of obstruction, and clearly marked.
 - 2. Copies of Safety Data Sheets (SDS) for all components shall be kept on site for review by the EH&S, department of health, or responsible party.

- C. Waste Disposal: There shall be adequate disposal on jobsite for non-hazardous waste generated during installation of the system.
- D. Handling
 - 1. All Safety Data Sheets shall be adhered to at all times.
 - 2. No untrained personnel shall touch, relocate, or use the materials without proper training or supervision.
 - 3. No congregating, eating, smoking, or drinking of any kind allowed on or near the materials. All materials are to be treated as dangerous substances without firsthand knowledge.

1.9 FIELD CONDITIONS

- A. Site Requirements
 - 1. Application may proceed while air, material, and substrate temperatures are between 40°F and 90°F providing the substrate temperature is above the dew point. Outside of this range, the Manufacturer shall be consulted.
 - 2. The ambient relative humidity in the specific location of the application shall be less than 85% and the surface temperature shall be at least 5°F above the dew point.
 - 3. Approved Applicator shall ensure that adequate ventilation is available for the work area.
 - 4. Approved Applicator shall be supplied with adequate lighting equal to the final lighting level during the preparation and installation of the system.
 - 5. Approved Applicator shall provide its own power or any necessary equipment to get the job done correctly and in a timely manner.
 - 6. Job area shall be free of other trades during and, for a period of 24 hours, after installation.
- B. Safety Requirements
 - 1. All open flames and spark-producing equipment shall be removed from the work area prior to commencement of application.
 - 2. "No Smoking" signs shall be posted at the entrances to the work area.
 - 3. The Facility Owner shall be responsible for the removal of foodstuffs from the work area.
 - 4. Non-related personnel in the work area shall be kept to a minimum.
- C. Existing Concrete Substrate
 - 1. Measure compressive strength according to ASTM C805. Acceptable results: $\geq 3,000$ psi.
 - 2. Measure pH according to Test Method ASTM F710. Acceptable Results: 8-14.
 - 3. If contamination is present or suspected, test and evaluate slab. Acceptable methods include, but are not limited to, petrographic examination according to ASTM C856 and solvent extraction to analyze compounds that may affect coating's ability to bond.
 - 4. The Facility Owner, Engineer, and/or General Contractor must be notified and advised of potential additional costs of testing to meet Manufacturer specifications.
- D. Moisture Testing shall be conducted as follows:
 - 1. Perform anhydrous calcium chloride test, ASTM F1869-98. Application will proceed only when the MVER (moisture vapor emission rates) is less than or equal to 3 lbs./1,000 SF/24 hrs.
 - 2. Perform RH (relative humidity) test using in situ probes, ASTM F2170. Application will proceed only when the RH level is less than or equal to 80%.
 - 3. If vapor emission exceeds the Manufacturer's specified RH or MVER requirements, the Facility Owner, Engineer, and/or General Contractor must be notified of potential additional costs to lower moisture values to meet Manufacturer's specifications.

PART 2 PRODUCTS

2.1 MANUFACTURER

- A. KRETUS® Inc., 1055 W. Struck Ave, CA 92867 (info@kretus.com, 714.694.2061, kretus.com).

2.2 MATERIALS REQUIRED FOR SYSTEM SPECIFIED

- A. Color(s) determined by Architect/Facility Owner
- B. Top coat texture is to be determined by KRETUS® Technical Representative and based on system requirements. Recommended textures include
1. 50/50 blend of KRETUS® ANTI-SLIP BEAD 50 AND BEAD 100
 2. KRETUS® ANTI-SLIP TEX 50
- C. BASE AND TOP COAT
1. KRETUS® SB ACRYLIC SEALER is a solvent-based, single-component copolymer acrylic blend.
 - a. Recommended Application Temperature: 35-85°F, <80% RH
 2. Texture: See 2.2.B.

2.3 PRODUCT REQUIREMENTS

- A. BASE AND TOP COAT

PROPERTY	TEST METHOD	TYPICAL VALUES
Abrasion Resistance	ASTM D4060	40 mg loss
Adhesion to Concrete	ASTM D4541	300 psi
Flame Spread/Critical Flux	ASTM E648	Class 1
Flame Spread/Rate of Burning	ASTM D635	Self-extinguishing
Heat Resistance Limitation		140-200°F
Moisture Vapor Emission Rate	ASTM F1869	<3 lbs.
Oil Absorption	MIL-D-3134	0.04%
Relative Humidity	ASTM F2170	<80%
Shore D Hardness	ASTM D2240	70-75
Water Absorption	ASTM D570	0.04%

2.4 RELATED MATERIALS

- A. Repair Materials: Use these products to repair surface imperfections before installation.
1. Shallow fill/patching (<1/4" deep)
 - a. KRETUS® Top Shelf® Epoxy
 - b. KRETUS® Urethane Polymer Concrete SL
 2. Deep fill/patching (>1/4" deep)
 - a. KRETUS® TOP SHELF® EPOXY EZ PATCH
 - b. Combine 64 oz of KRETUS® TOP SHELF® EPOXY Part A, 32 oz KRETUS® TOP SHELF® EPOXY Part B, and 40-50 lbs. of 30-mesh Manufacturer-approved clean, kiln-dried sand.
 - c. Combine standard 41-lb. kit of KRETUS® URETHANE POLYMER CONCRETE SL with 25-30 lbs. of 30-mesh Manufacturer-approved clean, kiln-dried sand.
 - d. Combine standard 56-lb. kit of KRETUS® URETHANE POLYMER CONCRETE MF with 10-15 lbs. of 30-mesh Manufacturer-approved clean, kiln-dried sand.
- B. Joint and Crack Fill Materials: Use these materials after installation.
1. Saw Cut Contraction/Construction Joint Filler and Crack Filler

- a. KRETUS® POLY JOINT FILLER (indoor only)
 - b. KRETUS® TOP SHELF® EPOXY EZ PATCH
 - c. Combine 64 oz of KRETUS® TOP SHELF® EPOXY Part A, 32 oz KRETUS® TOP SHELF® EPOXY Part B, and 40-50 lbs. of 30-mesh Manufacturer-approved clean, kiln-dried sand.
 - d. Combine standard 41-lb. kit of KRETUS® URETHANE POLYMER CONCRETE SL with 25-30 lbs. of 30-mesh Manufacturer-approved clean, kiln-dried sand.
 - e. Combine standard 56-lb. kit of KRETUS® URETHANE POLYMER CONCRETE MF with 10-15 lbs. of 30-mesh Manufacturer-approved clean, kiln-dried sand.
2. Color to match adjacent finished surfaces.
- C. Prime Coat: Required when concrete is very porous, in poor condition, or when outgassing is suspected or prevalent.
1. KRETUS® SOLVENT-BORNE ACRYLIC SEALER
 - a. Apply with a non-shed nap roller. (Yields 200-600 sf per 1 gallon.)
- D. Application Tools
1. **3/8" non-shed nap roller:** Jon-Don Part # RC-WOR64218-EA, Pro/Doo-Z Roller Cover, 18", 3/8" nap
- E. All other materials must be manufactured by or approved for use by KRETUS® (info@kretus.com, 714-694-2061, kretus.com).

PART 3 EXECUTION

3.1 EXAMINATION

- A. Coordinate with adjacent trades to ease construction process.
- B. Verify project site conditions under Section 01 00 00.
- C. Before starting installation, correct all unsatisfactory conditions.

3.2 SURFACE PREPARATION

- A. Prevent damage to substrate during preparation.
- B. Mechanically prepare concrete to ICRI CSP 3. Required CSP may vary based on the condition of concrete. Always adhere to International Concrete Repair Institute's current standards.
- C. Shotblast with mobile steel shot and dust recycling machine using a 50/50 blend of 290/330 shot. Remove steel shots with MAG-Broom and remove any leftover dust, debris, and loose particles using a dust collector vacuum with wand adapter. If using a small 110V shot-blaster, this step may need to be repeated several times by cross-blasting.
- D. Edge Grinding: Grind all edges using an adjustable speed grinder to ensure all edges are clear of paints, sealers, and contaminants. Do not grind at high speed, as this may smooth out pores of the concrete and does not allow system to properly adhere to substrate.
- E. Cleaning and Dust Removal: Wear shoe covers. Remove all leftover dust and any loose particles by using dust collector. Completely remove all existing coatings, oil, water, adhesives, dust, debris, and other substances that may impede system's adhesion.

3.3 MIXING



- A. Follow Manufacturer's printed instructions. Careful measurements and thorough mixing are essential for a proper cure.
- B. Review KRETUS® Mixing Station Guide for general handling, storage, and preparation procedures.

3.4 APPLICATION

- A. General
 - 1. Follow Manufacturer's printed instructions.
 - 2. Materials shall be applied in 2 distinct step(s):
 - a. BASE COAT
 - b. TOP COAT
 - 3. It is essential to read through and understand all Manufacturer application guidelines and methods and the proper use of the application equipment.
 - 4. Immediately prior to the application of any part of the system, the surface prepared shall be clean, dry, free of any contaminations, and any remaining dust or loose particles shall be removed using a vacuum.
 - 5. The handling, mixing, and addition of components shall be performed in a safe manner to achieve the desired results in accordance with experiences of the materials and working condition.
 - 6. The system shall follow the contour of the substrate unless the Architect has specified pitching or other leveling work.
 - 7. A neat finish with well-defined boundaries and straight edges shall be provided by the Applicator.
- A. BASE COAT
 - 1. Mix coating according to manufacturer instructions.
 - 2. Apply coating with a 3/8" nap non-shed roller. (Yields 200-600 SF per 1 gallon.)
- B. TOP COAT
 - 1. Mix coating according to manufacturer instructions.
 - 2. Apply coating with a 3/8" nap non-shed roller. (Yields 200-600 SF per 1 gallon.)
- C. Integral Cove Base (only if specified):
 - 1. Unless otherwise indicated or scheduled, provide integral cove base at 4" or 6" high by 1/8" thick with a 3/4" radius.
 - 2. Follow Manufacturer application guidelines. Provide cove base cap strip if specified.

3.5 JOINT CUTTING, PREPARATION, AND FILLING

- A. Coatings tend to pull away from free edges, termination points (anywhere concrete ends), joints, cracks, gutters, drains. Anchor joints may need to be added 6" from termination points. Joints and cracks may need to be expanded to 2x the width and 1x the depth. Edges around drains and gutters may need a deeper slope.
- B. Honor all existing joints. Locate original joint locations and sawcut through coating into the original joint. Saw blade must penetrate to the depth of the original joint or 2" deep, whichever is smaller. Prefill joints greater than 2" deep.
- C. Ensure sawcut joint is completely free of dust/debris/laitance.
- D. Avoid trapping air when installing joint filler: Fill joint from bottom to top. Slightly overfill to a crowned profile. After sufficient cure, shave excess filler. Filler profile should be flush with floor surface when dry. If filler profile is low/concave, remove top 1/2" of filler and re-apply.

3.6 FIELD QUALITY CONTROL

- A. The following tests and reporting shall be conducted by the Approved Applicator:
 - 1. condition of the area being installed
 - 2. temperature: date & time, air temperature, concrete surface temperatures, dew point
 - 3. product installed & coverage rates
 - 4. batch number of all materials
 - 5. project report shall be submitted upon completion of the work
- B. Adhesion tests of primer coat to the concrete per ASTM D7234 must show substrate failure with a minimal pull of 200 psi.
- C. Replica of the system as installed must be provided to Manufacturer for approval and warranty.
- D. Facility Owner reserves the right to invoke material testing procedures at any time and any number of times during the application process.
- E. Facility Owner may engage service of an independent testing laboratory to sample materials being used on the jobsite. Samples of material may be taken, identified, and certified in the presence of the Approved Applicator.

3.7 CURING, PROTECTION, AND CLEANING

- A. Cure flooring material in compliance with Manufacturer's instructions, taking care to prevent their contamination during stages of application and prior to completion of the curing process.
- B. Protection: After completion of application and clean up, do not allow heavy traffic on coated surfaces for a period of 24 hours at 75°F. Typical resinous floor coatings will take 7-14 days to fully cure.
- C. Cleaning: Perform detail cleaning at floor termination to leave cleanable surface for subsequent work of other sections. Remove any materials or spillage from site. Clean any uncured areas with suitable solvent. Dispose of any temporary floor covering and leftover materials in accordance with federal, local, and building requirements.

END OF SECTION